



SUBJECT Chemical Test

TEST LOCATION TÜV SÜD China

TÜV SÜD Products Testing (Shanghai) Co., Ltd.
B-3/4, No.1999 Du Hui Road, Minhang District
Shanghai 201108, P.R. China

CLIENT NAME Shandong Intco Medical Products Co., Ltd.

CLIENT ADDRESS No. 9888 Qiwang Road, Naoshan Industry Park, Qingzhou, Shandong, China

TEST PERIOD 25-Aug-2022~ 01-Sep-2022

RESULT SUMMARY

The tested items **complied with** European Resolution Res AP (2004) 4 on rubber products intended to come into contact with foodstuffs, Decree of 21 Mar 1973 on the hygiene of packaging, containers and utensils intended to come into contact with foodstuffs or with substances for personal use.

- Overall migration test

PASS

Prepared By


Minnie Gu

(Minnie Gu)
Report Drafter

Authorized By

Leo Liu

(Leo Liu)
Authorized Signatory



Note: (1) General Terms & Conditions as mentioned overleaf. (2) The results relate only to the items tested.(3) The test report shall not be reproduced except in full without the written approval of the laboratory.(4) Without the agreement of the laboratory, the client is not authorized to use the test results for unapproved propaganda.

RECEIPT DATE / TEST DATE

25-Aug-2022/ 25-Aug-2022

THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED

BY/ ON BEHALF OF THE CLIENTS AS

Sample Name: Disposable Nitrile Gloves
Sample Specification: Blue
Batch No./Date: /
Manufacturer: Shandong Intco Medical Products Co., Ltd.

SAMPLE NO.	DESCRIPTION	PHOTOGRAPH
721674489	Blue glove	

TEST RESULT(S)

Note: The migration results in this report were tested and expressed based on single use articles

- Overall Migration Test
 - Test method: With reference to EN 1186-5:2002
 - Migration ratio(S/V): 10dm²/L

Simulant (s) Used	Test Condition	Result(s) [mg/dm ²]	Maximum Permissible Limit [mg/dm ²]
3% Acetic acid	40°C for 2 hours	6.25	10

Note: This report is for internal use only such as internal scientific research ,education, quality control, product R&D.

-END OF THE TEST REPORT-



SUBJECT Chemical Test

TEST LOCATION TÜV SÜD China

TÜV SÜD Products Testing (Shanghai) Co., Ltd.
B-3/4, No.1999 Du Hui Road, Minhang District
Shanghai 201108, P.R. China

CLIENT NAME Shandong Intco Medical Products Co., Ltd.

CLIENT ADDRESS No.9888 Qiwang Road, Naoshan Industry Park, Qingzhou, Shandong, China

TEST PERIOD 04-Dec-2020~18-Dec-2020

RESULT SUMMARY The tested items **complied with** European Resolution Res AP (2004) 4 on rubber products intended to come into contact with foodstuffs.

- Overall migration test (20% Ethanol, Iso-octane) **PASS**
- Specific migration of Primary Aromatic Amine **PASS**
- Specific migration of N-nitrosamines and N-nitrosatable substances **PASS**

Prepared By

Judy hu

(Judy Hu)
Report Drafter



(Leo Liu)
Authorized Signatory

Note: (1) General Terms & Conditions as mentioned overleaf. (2) The results relate only to the items tested.(3) The test report shall not be reproduced except in full without the written approval of the laboratory.(4) Without the agreement of the laboratory , the client is not authorized to use the test results for unapproved propaganda.



RECEIPT DATE / TEST DATE

04-Dec-2020/ 04-Dec-2020

THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED

BY/ ON BEHALF OF THE CLIENTS AS

Sample Name: Disposable Nitrile Gloves(NBR)
Sample Type: M
Batch No./Date: /
Manufacture: Shandong Intco Medical Products Co., Ltd.

SAMPLE NO.	DESCRIPTION	PHOTOGRAPH
721660237	Blue glove	

TEST RESULT(S)

Note: The migration results in this report were tested and expressed based on single use articles.

1. Overall Migration Test

- Test method: In accordance with Europe Resolution Res AP (2004) 4 on rubber to be used for food contact applications, With reference to EN 1186: Part 5 (Test methods for overall migration into aqueous food stimulants by cell)/ EN 1186: Part 14 (substitute test).
- Migration ratio(S/V):10 dm² /L

Simulant(s) Used	Test Condition	Result(s) [mg/dm ²]	Maximum Permissible Limit [mg/dm ²]
20% Ethanol	70°C for 2 hours	10.4*	10
Iso-octane	40°C for 0.5 hour	1.30	10

Note: 1. * denotes the material or article that exceeds the overall migration limit by an amount not greater than the analytical tolerance mentioned below should therefore be deemed to be in EN 1186-1:2002

The following analytical tolerances have been observed:

- 20 mg/kg or 3 mg/dm² in migration tests using all fatty food simulants or substitutes,
- 6 mg/kg or 1 mg/dm² in migration tests using all aqueous food simulants.





2. Specific migration of Primary Aromatic Amine

- Test method: With reference to EN 13130-1:2004, followed by Kunststoffe im Lebensmittelverkehr, Book 2, Teil B II,XXI
- Test condition: 3% Acetic acid, 40°C for 2 hours
- Migration ratio(S/V): 6dm² /L

Test Item(s)	Result(s) [mg/kg]	Maximum Permissible Limit [mg/kg]
Primary Aromatic Amine	<0.01	0.01

3. Specific migration of N-nitrosamines and N-nitrosatable substances

- Test method: Sample preparation with reference to EN 12868:1999, followed by analysis using GC-MS
- Test condition: 3% Acetic acid, 40°C for 24 hours

Test Item(s)	Result(s) [mg/kg]	Detected limit [mg/kg]	Maximum Permissible Limit [mg/kg]
N-nitrosamines	ND	0.01	0.01
N-nitrosatable substances	ND	0.1	0.1

Note: 1. ND denotes not detected and less than Detected limit

2. Tested N-nitrosamines are listed below:

	Compounds name	Abbreviation	CAS#
1	N-Nitrosodimethylamine	NDMA	62-75-9
2	N-nitrosodiethylamine	NDEA	55-18-5
3/4	N-nitrosopyrrolidine or N-nitroso N-methyl N-phenylamine	NPYR or NMPHA	930-55-2 or 614-00-6
5	N-nitrosomorpholine	NMOR	59-89-2
6	N-Nitrosodi-n-propylamine	NDPA	621-64-7
7	N-nitrosopiperidine	NPIP	100-75-4
8	N-nitroso N-ethyl N-phenylamine	NEPhA	612-64-6
9	N-Nitrosodi-n-butylamine	NDBA	924-16-3
10	N-nitrosodibenzylamine	NDBzA	5336-53-8
11	N-Nitrosodiisononylamine	NDiNA	1207995-62
12	N-nitrosomethylethylamine	NMEA	10595-95-6
13	N-nitrosodiisobutylamine	NDiBA	997-95-5

Note: This report is for internal use only such as internal scientific research ,education, quality control, product R&D.

-END OF THE TEST REPORT-





SUBJECT Chemical Test

TEST LOCATION TÜV SÜD China
TÜV SÜD Products Testing (Shanghai) Co., Ltd.
B-3/4, No.1999 Du Hui Road, Minhang District
Shanghai 201108, P.R. China

CLIENT NAME Shandong Intco Medical Products Co., Ltd

CLIENT ADDRESS No.9888 Qiwang Road, Naoshan Industry Park, Qingzhou, Shandong, China

TEST PERIOD 16-Jan-2023~01-Feb-2023

RESULT SUMMARY The tested items **complied with** German Food & Feed Acts of September 1, 2005 (LFGB), Section 30 and 31 and BFR Recommendations XXI/1.

- Overall migration test **PASS**
- Sensory test **PASS**

Prepared By


Judy hu

(Judy Hu)
Report Drafter

Authorized By

Leo Liu

Authorized Signatory



Note: (1) General Terms & Conditions as mentioned overleaf. (2) The results relate only to the items tested.(3) The test report shall not be reproduced except in full without the written approval of the laboratory.(4) Without the agreement of the laboratory , the client is not authorized to use the test results for unapproved propaganda.

SAMPLE SOURCE/ RECEIPT DATE / TEST DATE

Logistics Express/ 16-Jan-2023/ 16-Jan-2023

THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED

BY/ ON BEHALF OF THE CLIENTS AS

Sample Name: COOP NHW blue nitrile disposable gloves
Sample Specification: S
Batch No./Date: IN22016627
Manufacturer: Shandong Intco Medical Products Co., Ltd

SAMPLE NO.	DESCRIPTION	PHOTOGRAPH
721677961	Blue gloves	

TEST RESULT(S)

Note: The migration results in this report were tested and expressed based on single use articles.

1. Overall Migration Test

- Test method: With reference to EN 1186-2:2022/ EN 1186-3:2022 .
- Migration ratio(S/V): 10dm²/L

Simulant(s) Used	Test Condition	Result(s) [mg/dm ²]	Maximum Permissible Limit [mg/dm ²]
3% Acetic acid	40°C for 0.5 hour	<3.00	10
10% Ethanol	40°C for 0.5 hour	<3.00	10
Olive oil	40°C for 0.5 hour	<3.00	10

- Test method: With reference to EN 1186-3:2022 and BFR Recommendations XXI/1
- Migration ratio(S/V): 5dm²/L

Simulant(s) Used	Test Condition	Result(s) [mg/dm ²]	Maximum Permissible Limit [mg/dm ²]
3% Acetic acid	40°C for 10 min	<3.00	10



2. Sensory test

- Test method: With reference to DIN 10955:2004.
- The submitted sample was simulated in distilled water at 40°C for 0.5 hour. After this treatment treated water was examined by panels with regard to any divergence in smell and taste.

Sample(s)	Testing Parameter	Grading result(s)	Recommended level
721677961	Transfer of taste	0	<3
	Transfer of smell	0	<3

- Note:
1. Available grading are listed as follow:
Grading 0: No perceptible taste/smell deviation
1: Just perceptible taste/smell deviation
2: Weak taste/smell deviation
3: Clear taste/smell deviation
4: Strong taste/smell deviation

Whole product:



Note: This report is for internal use only such as internal scientific research ,education, quality control, product R&D.

-END OF THE TEST REPORT-





SUBJECT Chemical Test

TEST LOCATION TÜV SÜD China
TÜV SÜD Products Testing (Shanghai) Co., Ltd.
B-3/4, No.1999 Du Hui Road, Minhang District
Shanghai 201108, P.R. China

CLIENT NAME Shandong Intco Medical Products Co., Ltd

CLIENT ADDRESS No.9888 Qiwang Road, Naoshan Industry Park, Qingzhou, Shandong, China

TEST PERIOD 31-May-2021~07-Jun-2021

RESULT SUMMARY

1. The tested items complied with German Food & Feed Acts of September 1, 2005 (LFGB), Section 30 and 31.	
- Overall migration test	PASS
- Color release	PASS
- Extractable formaldehyde	PASS
- Total lead and zinc content	PASS
- Sensory test	PASS
2. The tested items complied with AfPS GS 2019: 01 PAK	
- Polycyclic Aromatic Hydrocarbons (PAHs) content(Category 1)	PASS
3. As per client's request	
- Total Cadmium content	PASS

Prepared By

Nance Gao

(Nance Gao)
Report Drafter

Authorized By

Leo Li

(Leo Li)
Authorized Signatory



Note: (1) General Terms & Conditions as mentioned overleaf. (2) The results relate only to the items tested.(3) The test report shall not be reproduced except in full without the written approval of the laboratory.(4) Without the agreement of the laboratory , the client is not authorized to use the test results for unapproved propaganda.

RECEIPT DATE / TEST DATE

31-May-2021/ 31-May-2021

THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED

BY/ ON BEHALF OF THE CLIENTS AS

Sample Name: Disposable Nitrile Gloves
Sample Specification: /
Batch No./Date: /
Manufactory: Shandong Intco Medical Products Co., Ltd

SAMPLE NO.	DESCRIPTION	PHOTOGRAPH
721664284	Blue glove	

TEST RESULT(S)

Note: The migration results in this report were tested and expressed based on single use articles.

1. Overall Migration Test

- In accordance with BFR Recommendations XXI
- Test method: With reference to EN 1186: Part 4 (Test methods for overall migration into olive oil by cell), EN 1186: Part 5 (Test methods for overall migration into aqueous food stimulants by cell) and BFR Recommendations XXI
- Migration ratio (S/V): 10dm²/L

Simulant(s) Used	Test Condition	Result(s) [mg/dm ²]	Maximum Permissible Limit [mg/dm ²]
3% Acetic acid	40°C for 0.5 hours	3.15	10
10% Ethanol	40°C for 2 hours	0.950	10
Olive oil	40°C for 2 hours	<0.500	10

2. Color release

- Test method: With reference to Kunststoffe im Lebensmittelverkehr Book II, Teil B II, IX

Simulant(s) Used	Test Condition	Result(s)	Permissible Limit
10% Ethanol	50°C for 5 hours	No bleeding	No bleeding
2% Acetic acid	50°C for 5 hours	No bleeding	No bleeding
Peanut oil	50°C for 5 hours	No bleeding	No bleeding
Water	50°C for 5 hours	No bleeding	No bleeding

- Note:
1. No bleeding denotes no difference was found between blank and sample
 2. Bleeding denotes staining was found from sample



3. Extractable formaldehyde

- Test method: For compliance with the Recommendation of the BfR "Kunststoffe im Lebensmittelverkehr" Part XXI. Commodities based on Natural and Synthetic Rubber
- With reference to Section 2.7.1 of methods for the "Testing of commodities made of rubber"
- Test condition: 3% Acetic acid, 40°C for 0.5 hours
- Migration ratio (S/V): 6dm²/L

Test Item(s)	Result(s) [µg/ml]	Maximum Permissible Limit [µg/ml]
Extractable Formaldehyde	<0.5	3

4. Total lead and zinc content

- Test method: Acid digestion, then followed by ICP-OES

Test Item(s)	Result(s) [%]	Maximum Permissible Limit [%]
Lead content	<0.001	0.003
Zinc content	0.250	3.0

5. Sensory test

- Test method: With reference to DIN 10955.
- The submitted sample was simulated in distilled water at 40°C for 2 hours. After this treatment treated water was examined by panels with regard to any divergence in smell and taste.

Sample(s)	Testing Parameter	Grading result(s)	Recommended level
721664284	Transfer of taste	0	<3
	Transfer of smell	0	<3

Note: 1. Available grading are listed as follow:

- Grading 0: No perceptible taste/smell deviation
- 1: Just perceptible taste/smell deviation
- 2: Weak taste/smell deviation
- 3: Clear taste/smell deviation
- 4: Strong taste/smell deviation

6. Polycyclic Aromatic Hydrocarbons (PAHs) content

- Test method: In accordance with AfPS GS 2019: 01 PAK

Compounds	Results [mg/kg]	Detection Limit [mg/kg]
Chrysene	ND	0.01
Benzo[a]anthracene	ND	0.01
Benzo[b]fluoranthene	ND	0.01
Benzo[j]fluoranthene	ND	0.01
Benzo[k]fluoranthene	ND	0.01
Benzo[e]pyrene	ND	0.01
Benzo[a]pyrene	ND	0.01
Indeno[1,2,3-cd]pyrene	ND	0.01
Dibenzo[ah]anthracene	ND	0.01
Benzo[ghi]perylene	ND	0.01
Naphthalene	0.0585	0.01
Phenanthrene	0.0619	0.01





Anthracene	ND	0.01
Fluoranthene	0.0109	0.01
Pyrene	0.0321	0.01
Sum of Phenanthrene, Pyrene, Anthracene and Fluoranthene	0.105	--
Group PAH	0.163	--
Category as in AfPS GS 2019: 01 PAK	Category 1	--

Note: 1. ND denotes not detected, less than Reporting Limit
Limits and Categories for PAH in product according to AfPS GS 2019: 01 PAK

Limits and Categories

Parameter [mg/kg]	Category 1		Category 2		Category 3	
	Materials intended to be put in the mouth, or materials of toys from 2009/48/EC for children aged < 3 years with intended skin contact (contact >30s)		Products for use by children aged < 14 years (active or passive direct contact)	All other products acc to ProdSG	Products for use by children aged < 14 years (active or passive direct contact)	All other products acc to ProdSG
Benzo[a]pyrene	<0.2	<0.2	<0.2	<0.5	<0.5	<1
Benzo[e]pyrene	<0.2	<0.2	<0.2	<0.5	<0.5	<1
Benzo[a]anthracene	<0.2	<0.2	<0.2	<0.5	<0.5	<1
Benzo[b]fluoranthene	<0.2	<0.2	<0.2	<0.5	<0.5	<1
Benzo[j]fluoranthene	<0.2	<0.2	<0.2	<0.5	<0.5	<1
Benzo[k]fluoranthene	<0.2	<0.2	<0.2	<0.5	<0.5	<1
Chrysene	<0.2	<0.2	<0.2	<0.5	<0.5	<1
Dibenzo[a,h]anthracene	<0.2	<0.2	<0.2	<0.5	<0.5	<1
Benzo[ghi]perylene	<0.2	<0.2	<0.2	<0.5	<0.5	<1
Indeno[1,2,3-cd]pyrene	<0.2	<0.2	<0.2	<0.5	<0.5	<1
Phenanthrene, Anthracene, Fluoranthene and Pyrene	<1 sum	<5 sum	<10 sum	<20 sum	<50 sum	<50 Sum
Naphthalene	<1	<2		<10		
Sum 15 PAH	<1	<5	<10	<20	<50	

* Definition "short-term repetitive contact with the human skin" from REACH Annex XVII No. 50 amendment (COMMISSION REGULATION (EU) No 1272/2013)

7. Total Cadmium content

- Test method: Sample digested, analysed by ICP-MS

Test Item(s)	Result(s) [mg/kg]	Maximum Permissible Limit* [mg/kg]
Total Cadmium Content	<2	2





Note: 1. * denotes Maximum Permissible Limit was provided by client

Note: This report is for internal use only such as internal scientific research ,education, quality control, product R&D

-END OF THE TEST REPORT-



SHAI) CO



SUBJECT Chemical Test

TEST LOCATION TÜV SÜD China

TÜV SÜD Products Testing (Shanghai) Co., Ltd.
B-3/4, No.1999 Du Hui Road, Minhang District
Shanghai 201108, P.R. China

CLIENT NAME Shandong Intco Medical Products Co., Ltd.

CLIENT ADDRESS No.9888 Qiwang Road, Naoshan Industry Park, Qingzhou, Shandong, China

TEST PERIOD 09-Dec-2019~13-Dec-2019

TEST REQUEST In accordance with Council of Europe Res AP (2004) 4 on rubber to be used for food contact applications
- Overall Migration Test

RESULT SUMMARY The tested items **complied with** Council of Europe Res AP (2004) 4 on rubber to be used for food contact applications.
- Overall Migration Test (50% Ethanol)

PASS

Prepared By

Cynthia Cao

(Cynthia Cao)
Report Drafter

Authorized By

Leo Liu

(Leo Liu)
Authorized Signatory



Note: (1) General Terms & Conditions as mentioned overleaf. (2) The results relate only to the items tested. (3) The test report shall not be reproduced except in full without the written approval of the laboratory. (4) Without the agreement of the laboratory, the client is not authorized to use the test results for unapproved propaganda.




RECEIPT DATE / TEST DATE

09-Dec-2019/ 09-Dec-2019

**THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED
BY/ ON BEHALF OF THE CLIENTS AS**

Sample Name: Disposable Nitrile Gloves
Sample Specification: NA
Batch No./Date: NA
Manufacturer: NA
Packing Lot Number: NA
Dipping Lot Number: NA
Country of Origin: NA
Sales Destination(country): NA
Buyer: NA

SAMPLE NO.	DESCRIPTION	PHOTOGRAPH
721651170	Blue glove	



TEST METHOD(S)

- For material : Rubber
 - Overall migration test for compliance with Europe Resolution Res AP (2004) 4 on rubber to be used for food contact applications.
 - As specified in REGULATION (EU) No 10/2011 and its amendments; with reference to EN 1186: Part 5 (Test methods for overall migration into aqueous food stimulants by cell)

TEST RESULT(S)

- Overall Migration Test - with reference to EN 1186 : Part 5
 - Migration ratio: $S/V=10\text{dm}^2/\text{L}$

Simulant(s) Used	Test Condition#	Result(s) [mg/kg]	Maximum Permissible Limit [mg/kg]
50% Ethanol	40°C for 2 hours	6.68	60

Note: 1. # denotes test condition was provided by client

Note: This report is for internal use only by the client.

-END OF THE TEST REPORT-

Test Report

No. TAOHG2206459102 A01

Date: 21 Sep 2022

Page 1 of 3

Client Name : SHANDONG INTCO MEDICAL PRODUCTS CO.,LTD

Client Address : NO.9888,QIWANG ROAD,NAOSHAN INDUSTRY PARK,QINGZHOU,SHANDONG,CHINA

Sample Name : METRO PROFESSIONAL NITRILE GLOVES, NON-POWDERED,BLUE

Client Ref. Information : SIZE S, M, L, XL

The above sample(s) and information were provided by the client.

THIS REPORT IS TO SUPERSEDE TEST REPORT NO.TAOHG2206459101.

SGS Job No. : QDHL2209012394CW-01 - QD

Date of Sample Received : 02 Sep 2022

Testing Period : 02 Sep 2022 - 08 Sep 2022

Test Requested : Selected test(s) as requested by the client.

Test Method(s) : Please refer to next page(s).

Test Result(s) : Please refer to next page(s).

Result Summary :

Test Requested	Conclusion
French order of August 5,2020 - Overall migration	PASS

Signed for and on behalf of
SGS-CSTC Standards Technical Services (Qingdao) Co., Ltd.



Wang Bo, Claire
Approved Signatory

scan to see the report



TAOHG2206459102 A01



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.
Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

Test Report

No. TAOHG2206459102 A01

Date: 21 Sep 2022

Page 2 of 3

Test Result(s) :

Test Part Description :

Specimen No.	SGS Sample ID	Description	Material (claimed by the client)
SN1	TAO22-064591.001	Blue rubber glove	Nitrile rubber

Remarks :

- (1) mg/dm² = milligram per square decimeter
- (2) mg/kg = milligram per kilogram
- (3) °C= degree Celsius
- (4) < = less than
- (5) MDL = Method Detection Limit
- (6) ND = Not Detected (< MDL)

French order of August 5,2020 - Overall migration

Test Method : With reference to Commission Regulation (EU) No 10/2011 of 14 January 2011 Annex III and Annex V for selection of condition and EN 1186-1:2002 for selection of test methods; EN 1186-9: 2002 aqueous food simulants by article filling method.

<u>Simulant Used</u>	<u>Time</u>	<u>Temperature</u>	<u>Max. Permissible Limit</u>	<u>Result of 001 Overall Migration</u>	<u>Conclusion</u>
95% Ethanol (V/V) aqueous solution (Rectified olive oil substitute)	2.0hr(s)	40°C	10mg/dm ²	10.2mg/dm ²	PASS
Area/Volume			-	10.0dm ² /kg	

Notes :

- (1) Analytical tolerance of aqueous simulants is 2 mg/dm² or 12 mg/kg.
- (2) Test condition & simulant were specified by client.
- (3) Report the first migration result.
- (4) A material or article with overall migration result that exceeds the overall migration limit by an amount not exceeding the analytical tolerance, shall be deemed to be in compliance with the overall migration limit.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.
Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com



Note:

- This report updates test requirement.

Unless otherwise stated, the decision rule for conformity reporting is based on Binary Statement for Simple Acceptance Rule ($w=0$) stated in ILAC-G8:09/2019.

Sample photo:



SGS authenticate the photo on original report only

*** End of Report ***



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.
Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com



山东英科医疗制品有限公司
Shandong Intco Medical Products Co., Ltd.

文件编号 Doc No.

INTCO- NBR-FDOC

版本 Ver.

A1

Declaration of Conformity for Food Contact

Declares that the disposable Nitrile gloves, made of NBR latex as main material, that comply with the provisions of Regulation (EC) 1935/2004, (EU) 10/2011 and applicable national regulations. When used as specified, the overall migration and the specific migrations are below the legal limit according to Regulation (EU) 10/2011. Regulation (EU) No. 10/2011 does not apply to nitrile gloves with regard to the requirements for materials and raw materials, it is only applicable in relation to the migration tests.

The Nitrile gloves may be used safely for the preparation and handling of foodstuff.

Types of food with which it is intended to be put in contact have Food simulant A, B, D2.

Sinulants	Test condition	Results
Food simulant A(10% Ethanol)	40°C 2h	<10mg/dm ²
Food simulant B (3% Acetic acid)	40°C 30min	<10mg/dm ²
Food simulant D2 (Olive oil)	40°C 2h	<10mg/dm ²

Note: Restricted substances and dual-use substances are not included. For substances that are not included in the Union list (Annex I of Regulation (EU) 10/2011 in its current version), the national provisions such as the recommendation of BfR and the requirements of Section 31 (1) LFGB are still valid. The disposable nitrile examination gloves are consumer goods based on natural and synthetic rubber.

The above mentioned declaration of conformity is exclusively under the responsibility of

Company: Shandong Intco Medical Products Co., Ltd.

Address: Qiwang Road, Naoshan Industrial Park. Qingzhou, Shandong, China.

This Declaration of conformity is valid for three years: 6 / Jan / 2021 to 5 / Jan / 2024. If there is a change in the declaration information, this declaration is invalid.

Shandong 2021-06-07
张

Place , date

Rick Cheng Quality Manager

Legally binding signature, Function